



DESCRIPTION			
Total thickness	EN ISO 24346	mm	6.00
Thickness of wear layer	EN ISO 24340	mm	2
Weight	EN ISO 23997	g/m ²	9365
Tile size	EN ISO 24342	mm	635 x 635 (GTI Max Connect)
			600 x 600 (GTI Max Cleantech)
CLASSIFICATION			
Norm / Product specification	-	-	EN ISO 10582
European classification	EN ISO 10874	class	34 - 43
Fire rating	EN 13 501-1	class	Bfl-s1
Static electrical propensity	EN 1815	kV	< 2
Slip resistance wet: ramp test with oil	DIN 51130	class	R10
Pendulum test	BS7976	-	+36 PTV
			<table border="0"> <tr> <td>Concrete Emboss Colors : 0259 / 0260 / 0261 / 0262 / 0263 / 0268 / 1249</td> <td>Rice Emboss Colors : 0227 / 0228 / 0230 / 0231 / 0232 / 0233 / 0234 / 0235 / 0236 / 0247 / 0249 / 0252 / 0253 / 0255 / 0264 / 0265 / 0266 / 0267 / 0269</td> <td>Soft Emboss Colors : 2247 / 2249 / 2252 / 2264 / 2265 / 2266 / 2267</td> </tr> </table>
Concrete Emboss Colors : 0259 / 0260 / 0261 / 0262 / 0263 / 0268 / 1249	Rice Emboss Colors : 0227 / 0228 / 0230 / 0231 / 0232 / 0233 / 0234 / 0235 / 0236 / 0247 / 0249 / 0252 / 0253 / 0255 / 0264 / 0265 / 0266 / 0267 / 0269	Soft Emboss Colors : 2247 / 2249 / 2252 / 2264 / 2265 / 2266 / 2267	
PERFORMANCE			
Wear resistance	EN 660.2	mm ³	≤ 2
Wear group	-	group	T
Type Binder content	EN ISO 10582	type	I
Dimensional stability	EN ISO 23999	%	≤ 0.15
Residual indentation	EN ISO 24343-1	mm	≤ 0.10
Castor chair test (type H)	ISO 4918	-	OK
Shore hardness	EN ISO 868	H _b	≥ 50
Shifting resistance	CAHIER CSTB 3562	N/mm ²	≥ 30
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Color fastness	ISO 105 - B02	degree	≥ 6
Surface treatment	-	-	PUR+
Chemical products resistance	EN ISO 26987	-	OK
ENVIRONMENT / INDOOR AIR QUALITY			
TVOC after 28 days	ISO 16000-6	micrograms/m ³	< 10
Certification	-	-	Floorscore®
CE MARKING			
	EN 14041	-	
		-	